

Self-adhesive waterproofing membrane with glass fleece and reinforced PE foil carrier and with elastomere modified bitumen – non standard width

Product description IZOSELF PE plus-R 10, 20, 33 cm are a self-adhesive waterproofing membranes made from a glass fleece and reinforced PE foil carrier, on both sides coated with elastomere modified bitumen. The membrane is on one side protected with easily removable siliconized foil, on the other with polymeric sheeting.

Characteristics of the product IZOSELF PE plus-R 10, 20, 33 cm meets the demands of the standards SIST EN 13969 type A and SIST EN 13970. The high quality with SBS modified bituminous mass gives flexibility at low temperatures and extraordinary adhesion on the surface, especially on all thermal insulation materials, enabling a quick and clean installation. Reinforced PE film gives the product an additional resistance to mechanical stress and good vapor barrier.

Characteristic	EN Method	Unit	Declaration SIST EN 13969, SIST EN 13970
Reinforcement	glass fleece + polyethylene foil		
Surface protection	reinforcement polymeric sheeting / polymeric sheeting		
Length	1848-1	m	≥20
Width	1848-1	m	0,10 or 0,20 or 0,33 Toler.: -0,0; +0,005
Thickness	1848-1	mm	≥1,2
Straightness	1848-1	20mm/10m	pass
Water tightness	1928	kPa	≥10
Durability of water tightness against artificial ageing (12 weeks at 70°C)	1296/1928	kPa	≥2
Impact resistance	12691/A	mm	≥ 200
Low temperature flexibility	1109	°C	≤ -30
Resistance to tearing	12310-1	N	≥ 200
• longitudinal			≥ 200
• transversal			
Shear resistance of joints	12317-1	N/50 mm	≥ 400
• longitudinal			≥ 300
• transversal			
Water vapor transmission properties	1931	μ	≥ 100 000
Water vapor transmission properties	1931	m	≥ 150
Durability of water vapour resistance against artificial ageing	1296/1931	change	≤ 50%
Reaction to fire	13501-1	Class	E
Resistance to static loading	12730/B	kg	≥ 10
Chemical resistance	1847/13969 Annex A	-	pass
Tensile strength	12311-1	N/50mm	≥ 400
• longitudinal			≥ 300
• transversal			
Elongation (at break*)	12311-1	% /50mm	≥ 3,0 (≥200*)
• longitudinal			≥ 3,0 (≥200*)
• transversal			
Content of dangerous substances	Annex ZA	/	no

Use and installation

IZOSELF PE plus-R 10, 20, 33 cm can be applied to various areas of construction. Due to the strong reinforcement of PE foil is also suitable as steam in the prison systems of straight and slanted roofs, walls and other structural assemblies. It is used in places where performance is difficult because of limited space waterproofing and which should not be used as a way to install with open fire (to protect wooden structures from humidify, sealing gaps in the installation of doors and windows, installation of belts on the installation of insulation board core, making the different details of waterproofing, etc.). Not to be used in places where water is present under pressure. The product can be installed in such a way that removes the protective film and while pressure at the base. Prior to preparing the ground with coating IBITOL is recommended (except in cases of heat-insulation and other related bases). Self-adhesive property is activated after a prolonged impact of higher pressures above layers. When is expected and required immediate self-adhesive property as examples of vertical surfaces or other surfaces which do not appear higher temperatures, the installation of product used to increase the adhesiveness with hot air. This procedure is recommended in all overlapping cases of applications.

Storage

The rolls have to be stored in an upright position, protected against dampness and extreme temperatures. In winter it is recommended to store the rolls before installation for 24 hours at a temperature of over + 5°C.

Disposal considerations of waste

For the removal of waste of product it is necessary to follow the valid local environmental regulations.

The product is in conformity with **SIST EN 13970:2005 and SIST EN 13970:2005/A1:2007, SIST EN 13969:2005 and SIST EN 13969:2005/A1:2007 type A and SIST 1031:2011.**

Number EC certificate of control of quality: **1404 – CPD – 1059.**



10

The system of quality and handling of the environment is conform with **SIST EN ISO 9001 and 14001.**

Producer

FRAGMAT TIM d.d., Spodnja Rečica 77, SI - 3270 Laško ; www.fragmat.si

file:

Laško: Tel.: +386 (0)3 734 45 00 Fax.: +386 (0)3 734 45 63

Technical sheet

Ljubljana: Tel.: +386 (0)1 540 53 79 Fax.: +386 (0)1 524 86 94

IZOSELF PE plus-R/12-01