

IZOELAST REFLEX T5

Waterproofing membrane with a glass fabric carrier and with elastomere modified bitumen

Product description IZOELAST REFLEX T5 is a waterproofing membrane made from a glass fabric reinforcement that is coated on both sides with elastomere modified bitumen. The membrane is on the upper side protected by mineral granules and on the bottom side by polymeric sheeting.

Characteristics of the product IZOELAST REFLEX T5 meets the demands of the standards SIST EN 13707 and SIST 1031. Because of its excellent flexibility at low temperatures it shows excellent characteristics at installation and deformations, and excellently bridges cracks also at low temperatures. The mechanical characteristics of the reinforcement give the product high resistance against penetration and tearing, mineral granules protect it against UV-light and ageing.

Characteristic	EN Method	Unit	Declaration EN 13707
Reinforcement		Woven glass fabric	
Surface protection		mineral granules/ polymeric sheeting	
Length	1848-1	m	≥7,5
Width	1848-1	m	≥1
Straightness,	1848-1	20mm/10m	pass
Thickness	1849-1	mm	≥ 5,2
Water tightness	1928	kPa	≥ 200
Flexibility at low temperature			
Surface	1109	°C	≤ -10
Bottom			≤ -15
Flow resistance at elevated temperature	1110	°C	≥ 100
Resistance to tearing			
• longitudinal	12310-1	N	NPD
• transversal			
shear resistance of joints			
• longitudinal	12317-1	N/50 mm	NPD
• transversal			
Water vapour properties	1931	μ	20000
External fire performance	13501-5	Class	F _{ROOF} (t1)
Reaction to fire	13501-1	Class	E
Chemical resistance	1847/13707 Annex C	-	pass
Resistance to static loading	12730/A	kg	NPD
Resistance to impact	12691	mm	NPD
Tensile properties			
• longitudinal	12311-1	N/50mm	≥ 1000
• transversal			≥ 1500
Elongation			
• longitudinal	12311-1	%/50mm	≥ 2,0
• transversal			≥ 2,0
Flexibility at low temperature after artificial ageing by long term exposure to elevated temperature(12 weeks at 70 °C)	1296/1109	°C	≤ -10
Flow resistance at elevated temperature after artificial ageing by long term exposure to elevated temperature(12 weeks at 70 °C)	1296/1110	°C	≥ 90
Adhesion of granules	12039	%	≤ 30
Content of dangerous substances	Annex ZA	/	no

Use and installation IZOELAST REFLEX T5 is used regarding the demands of the standards in two- ore more layered waterproofing of flat roofs as top layer, protecting it against ageing and UV-light. It is applied by torching on the entire surface with 10 cm overlaps.

Storage The rolls have to be stored in an upright position, protected against dampness and extreme temperatures. In winter it is recommended to store the rolls before installation for 24 hours at a temperature of over + 5°C.

Disposal considerations of waste For the removal of waste of product it is necessary to follow the valid local environmental regulations.



The product is in conformity with **SIST EN 13707:2005+A2:2009** and **SIST 1031:2011** .

Number EC certificate of control of quality: **1404 – CPD – 1059**.

06

The system of quality and handling of the environment is conform with **SIST EN ISO 9001** and **14001**.

Producer

FRAGMAT TIM d.d., Spodnja Rečica 77, SI - 3270 Laško ; www.fragmat.si

file:

Laško: Tel.: +386 (0)3 734 45 00 Fax.: +386 (0)3 734 45 63

Technical sheet

Ljubljana: Tel.: +386 (0)1 540 53 79 Fax.: +386 (0)1 524 86 94

IZOELAST REFLEX T5/12-01