



# IZOTEKT P5 FLL plus

## Waterproofing membrane with a polyester carrier and with plastomer (APP) modified bitumen, resistant to the penetration of roots

### Product description

**IZOTEKT P5 FLL plus** is a waterproofing membrane made from a polyester reinforcement, on both sides coated with plastomer (APP) modified bitumen, to which additions are added that prevent the penetration of roots (membrane is not resistant to penetration of aggressive roots and other parts of the roots, such as Bamboo, which could be physically damaged membrane). The membrane is protected on both sides by an easily fusible film.

### Characteristics of the product

**IZOTEKT P5 FLL plus** meets the demands of the standards SIST EN 13707, 13969 type A and type T and SIST 1031. The APP additions give high resistance against ageing, UV-light and higher temperatures, as well as flexibility at low temperatures. The polyester reinforcement gives high elasticity and resistance to static and dynamic strains.

Characteristic	EN Method	Unit	Declaration SIST EN 13707, SIST EN 13969
Reinforcement		Polyester fleece	
Surface protection		polymeric sheeting / polymeric sheeting	
Length	1848-1	m	≥7,5
Width	1848-1	m	≥1
Straightness	1848-1	20mm/10m	pass
Thickness	1849-1	mm	≥ 4,5
Water tightness	1928	kPa	≥ 200
Durability of water tightness against artificial ageing (12 weeks at 70 ° C)	1296/1928	kPa	≥ 200
Flexibility at low temperature	1109	°C	< -10
Flow resistance at elevated temperature	1110	°C	≥ 120
Resistance to tearing			
• longitudinal	12310-1	N	≥ 200
• transversal			≥ 200
Shear resistance of joints			
• longitudinal	12317-1	N/50 mm	≥ 600
• transversal			≥ 550
Dimensional stability			
• longitudinal	1107-1	%	≤ 0,6
• transversal			≤ 0,6
Water vapour transmission properties	1931	μ	20000
Reaction to fire	13501-1	Class	E
External fire performance	13501-5	Class	F <sub>ROOF</sub> (t1)
Chemical resistance	1847/13707 Annex C	-	pass
Resistance to static loading	12730/A	kg	≥ 15
Resistance to static loading	12730/B	kg	≥ 20
Resistance to impact	12691/A	mm	≥ 1500
Resistance to impact	12691/B	mm	≥ 2000
Tensile properties			
• longitudinal	12311-1	N/50mm	≥ 700
• transversal			≥ 600
Elongation			
• longitudinal	12311-1	%/50mm	≥ 40,0
• transversal			≥ 40,0
Resistance to root penetration	13948	-	pass
Flexibility at low temperature after artificial ageing by long term exposure to elevated temperature(12 weeks at 70 ° C)	1296/1109	°C	NPD
Flow resistance at elevated temperature after artificial ageing by long term exposure to elevated temperature (12 weeks at 70 ° C)	1296/1110	°C	NPD
Content of dangerous substances	Annex ZA	/	no

### Use and installation

**IZOTEKT P5 FLL plus** is used regarding the demands of the standards as a finishing layer in green flat roof systems or as a layer in very demanding waterproofing of underground parts of objects that are exposed to water pressure and where resistance against root penetration is needed. Normally it is installed by torching on the entire surface or punctual with 10 cm overlaps.

### Storage Disposal

The rolls have to be stored in an upright position, protected against dampness and extreme temperatures. In winter it is recommended to store the rolls before installation for 24 hours at a temperature of over + 5°C.

### considerations of waste

For the removal of waste of product it is necessary to follow the valid local environmental regulations.



The product is in conformity with **SIST EN 13707:2005+A2:2009**, **SIST EN 13969:2005** and **SIST EN 13969:2005/A1:2007 type A and type T**, **SIST 1031:2011** .  
Number EC certificate of control of quality: **1404 – CPD – 1059**.

The system of quality and handling of the environment is conform with **SIST EN ISO 9001 and 14001**.

Producer

FRAGMAT TIM d.d., Spodnja Rečica 77, SI - 3270 Laško ; [www.fragmat.si](http://www.fragmat.si)

file:

Laško: Tel.: +386 (0)3 734 45 00 Fax.: +386 (0)3 734 45 63

tech.sheet.

Ljubljana: Tel.: +386 (0)1 540 53 79 Fax.: +386 (0)1 524 86 94

IZOTEKT P5 FLL plus/12-01