

# IZOTEKT V4 plus

## Waterproofing membrane with a glass fleece carrier and with plastomer (APP) modified bitumen

**Product description** IZOTEKT V4 plus is a waterproofing membrane made from a glass fleece reinforcement that is coated on both sides with plastomer (APP) modified bitumen. The membrane is protected on both sides by polymeric sheeting.

**Characteristics of the product** IZOTEKT V4 plus meets the demands of the standards SIST EN 13969 for type A and type T. The APP additions give high resistance against ageing, UV-light and higher temperatures, as well as flexibility at low temperatures. The glass fleece gives dimensional stability.

Characteristic	EN Method	Unit	Declaration SIST EN 13969
Reinforcement		Glass fleece	
Surface protection		polymeric sheeting / polymeric sheeting	
Length	1848-1	m	≥10
Width	1848-1	m	≥1
Straightness	1848-1	20 mm/10m	pass
Thickness	1849-1	mm	≥3,6
Water tightness	1928	kPa	≥ 60
Durability of water tightness against artificial ageing	1296/1928	kPa	≥ 60
Flexibility at low temperature	1109	°C	≤ -10
Resistance to tearing			
• longitudinal	12310-1	N	≥ 70
• transversal			≥ 70
Shear resistance of joints			
• longitudinal	12317-1	N/50 mm	≥ 350
• transversal			≥ 250
Water vapour properties	1931	μ	NPD
Reaction to fire	13501-1	Class	E
Chemical resistance	1847/13969 Annex A	-	pass
Resistance to static loading	12730/B	kg	≥ 5
Resistance to impact	12691/A	mm	≥ 900
Tensile properties			
• longitudinal	12311-1	N/50mm	≥ 350
• transversal			≥ 250
Elongation			
• longitudinal	12311-1	%/50mm	≥2,0
• transversal			≥2,0
Content of dangerous substances	Annex ZA	/	no

**Use and installation** IZOTEKT V4 plus is used regarding the demands of the SIST EN standards for less demanding one or more layered waterproofings of vertical or horizontal parts of objects that are exposed to water pressure. It can also be used as secondary roofing in systems of inclined roofs. The membrane is installed by torch with 10 cm overlaps.

**Storage** The rolls have to be stored in an upright position, protected against dampness and extreme temperatures. In winter it is recommended to store the rolls before installation for 24 hours at a temperature of over + 5°C.

**Disposal considerations of waste** For the removal of waste of product it is necessary to follow the valid local environmental regulations.



The product is in conformity with **SIST EN 13969:2005 and SIST EN 13969:2005/A1:2007 type A and type T and SIST 1031:2011.**

Number EC certificate of control of quality: **1404 – CPD – 1059.**

06

**The system of quality and handling of the environment is conform with SIST EN ISO 9001 and 14001.**