

IZOTEKT REFLEX P4

Waterproofing membrane with a polyester carrier and plastomer (APP) modified bitumen.

Product description IZOTEKT REFLEX P4 is a waterproofing membrane made from a polyester reinforcement that is coated on both sides with plastomer (APP) modified bitumen. The membrane is on the upper side protected by mineral granules and on the bottom side by polymeric sheeting.

Characteristics of the product IZOTEKT REFLEX P4 meets the demands of the standards SIST EN 13707 and SIST 1031. The additions of APP and the protection by mineral granules give high resistance against ageing, UV-light and higher temperatures and flexibility at low temperatures. The polyester reinforcement gives high elasticity and resistance to static and dynamic strains.

characteristic	EN Method	Unit	Declaration EN 13707
Reinforcement		Polyester fleece	
Surface protection		mineral granules/ polymeric sheeting	
Length	1848-1	m	≥7,5
Width	1848-1	m	≥1
Straightness	1848-1	20mm/10m	pass
Thickness	1849-1	mm	≥ 4,2
Water tightness	1928/2000	kPa	≥ 10
Flexibility at low temperature			
Surface	1109	°C	≤ -5
Bottom			≤ -10
Flow resistance at elevated temperature	1110	°C	≥ 120
Resistance to tearing			
• longitudinal	12310-1	N	NPD
• transversal			
Shear resistance of joints			
• longitudinal	12317-1	N/50 mm	NPD
• transversal			
Dimensional stability			
• longitudinal	1107-1	%	≤ 0,6
• transversal			≤ 0,6
Water vapour properties	1931	μ	20000
External fire performance	13501-5	/	NPD
Reaction to fire	13501-1	/	F
Chemical resistance	1847/13707 Annex C	-	pass
Resistance to static loading	12730/A	kg	NPD
Resistance to impact	12691	mm	NPD
Tensile properties			
• longitudinal	12311-1	N/50mm	600 -10%
• transversal			600 -10%
Elongation			
• longitudinal	12311-1	%/50mm	≥ 35,0
• transversal			≥ 35,0
Flexibility at low temperature after artificial ageing by long term exposure to elevated temperature(12 weeks at 70 °C)	1296/1109	°C	≤ 0
Flow resistance at elevated temperature after artificial ageing by long term exposure to elevated temperature(12 weeks at 70 °C)	1296/1110	°C	≥ 100
Adhesion of granules	12039	%	≤ 30

Use and installation IZOTEKT REFLEX P4 is used regarding the demands of the SIST EN standards as top layer in systems of two or more layered waterproofing of flat roofs that protects the roof against ageing and UV-light. It can be used as top layer in reconstructions of flat roofs. The membrane is installed by torching.

Storage The rolls have to be stored in an upright position, protected against dampness and extreme temperatures. In winter it is recommended to store the rolls before installation for 24 hours at a temperature of over + 5°C.



06

The product is in conformity with SIST EN 13707 and SIST 1031.

Number EC certificate of control of quality: **1404 – CPD – 1059**.

The system of quality and handling of the environment is conform with SIST EN ISO 9001 and 14001.

Producer

FRAGMAT TIM d.d., Spodnja Rečica 77, SI - 3270 Laško ; www.fragmat.si

file:

Laško: Tel.: +386 (0)3 734 45 00 Fax.: +386 (0)3 734 45 63

Technical sheet

Ljubljana: Tel.: +386 (0)1 540 53 79 Fax.: +386 (0)1 524 86 94

IZOTEKT REFLEX P4/10-01