



IZOTEKT REFLEX P5 plus

Waterproofing membrane with polyester, enforced with glass fibres and with plastomer (APP) modified bitumen

Product description

IZOTEKT REFLEX P5 plus is a waterproofing membrane made from a polyester reinforcement, with glass fibres enforced and on both sides coated with plastomer (APP) modified bitumen. The membrane is on the upper side protected by mineral granules and on the bottom side by polymeric sheeting.

Characteristics of the product

IZOTEKT REFLEX P5 plus meets the demands of the standards SIST EN 13707 and SIST 1031. The especially high quality additions of APP and a protection by mineral granules give high resistance against ageing, UV-light and higher temperatures and extraordinary flexibility at low temperatures. The polyester reinforcement combined with glass fibres gives high elasticity and resistance to static and dynamic strains, as well as extraordinary dimensional stability.

Characteristic	EN Method	Unit	Declaration EN 13707
Reinforcement		Polyester fleece	
Surface protection		mineral granules/ polymeric sheeting	
Length	1848-1	m	≥ 7,5
Width	1848-1	m	≥ 1
Straightness	1848-1	20mm/10m	pass
Thickness	1849-1	mm	≥ 5,5
Water tightness	1928/2000	kPa	≥ 10
Water tightness after stretching at low temperature			
• longitudinal	13897	%	≥ 10
• transversal			≥ 10
Flexibility at low temperature			
Surface	1109	°C	≤ -10
Bottom			≤ -15
Flow resistance at elevated temperature	1110	°C	≥ 130
Resistance to tearing			
• longitudinal	12310-1	N	≥ 300
• transversal			≥ 300
shear resistance of joints			
• longitudinal	12317-1	N/50 mm	≥ 800
• transversal			≥ 700
Peel resistance of joints			
• longitudinal	12316-1	N/50 mm	≥ 30/40
• transversal			≥ 20/25
Dimensional stability			
• longitudinal	1107-1	%	≤ 0,3
• transversal			≤ 0,3
Water vapour properties	1931	μ	20000
External fire performance	13501-5	/	NPD
Reaction to fire	13501-1	/	F
Chemical resistance	1847/13707 Annex C	-	pass
Resistance to static loading	12730/A	kg	≥ 15
Resistance to impact	12691	mm	≥ 100
Tensile properties			
• longitudinal	12311-1	N/50mm	≥ 800
• transversal			≥ 700
Elongation			
• longitudinal	12311-1	%/50mm	≥ 35,0
• transversal			≥ 35,0
Flexibility at low temperature after artificial aging by long term exposure to elevated temperature(12 weeks at 70 ° C)	1296/1109	°C	≤ -5
Flow resistance at elevated temperature after artificial aging by long term exposure to elevated temperature(12 weeks at 70 ° C)	1296/1110	°C	≥ 120
Adhesion of granules	12039	%	≤ 30

Use and installation

IZOTEKT REFLEX P5 plus is used regarding the demands of the SIST EN standards as top layer, most of all in the system of one-layered waterproofing of flat roofs. It can also be used as top layer in two or more layered waterproofing of flat roofs that protects the roof against ageing and UV-light, or as top layer in the restructuring of flat roofs. The membrane is installed by torching, but it can also be used in the installation of waterproofing by mechanical fastening to the surface. Overlapping: machine direction with a 12 cm, cross direction with a 15cm.

Storage

The rolls have to be stored in an upright position, protected against dampness and extreme temperatures. In winter it is recommended to store the rolls before installation for 24 hours at a temperature of over + 5°C.



06

The product is in conformity with SIST EN 13707 and SIST 1031.

Number EC certificate of control of quality: 1404 – CPD – 1059.

The system of quality and handling of the environment is conform with SIST EN ISO 9001 and 14001.

Producer

FRAGMAT TIM d.d., Spodnja Rečica 77, SI - 3270 Laško ; www.fragmat.si

file:

Laško: Tel.: +386 (0)3 734 45 00 Fax.: +386 (0)3 734 45 63

Technical sheet

Ljubljana: Tel.: +386 (0)1 540 53 79 Fax.: +386 (0)1 524 86 94

IZOTEKT REFLEX P5 plus/10-01